



robin

La qualité en peinture

Technical data sheet
Updated 26.01.2010

2K PU INDUSTRIE FINITION **TWO COMPONENTS POLYURETHANE FINISH PAINT**

Composition: Two components polyurethane and isocyanates finish paint.

Appearance: satin, gloss, mat.

Properties and use:

Can be applied by spraying, brush or roller with different hardener for every application.

Note : this system can also be made no skidding (see other notice).

Using Directories:

Prepare surface (ground) with a coat of 2KPU Industrie Fond L-12777.

1. Application by gun spray :

Mix component A (2L of paint) with component B (0,5L of hardener) L-12814..

Pot life 20°C : 24 h.

Spraying:

- 1,3 to 1,5 mm
 - 3 to 4 bars
 - application 40 micros dry
 - ideal viscosity 30 to 40 sec.
- DIN 4 mm / 20°C

Dilution: Thinner L-9118
5-10% for gun spray

2. Application brush and roller

Component A unchanged.

Component B L-18819 is used for brush and roller application.

Mix 2L of component A with 0,5L of hardener L-18819 component B (rapport 5-1 in volume).

Shake well hardener B!

It's necessary to wait 24 hours before applying second layer.

Pot life 20°C :24 h.

Drying:

gun spray : dust free: 15-20 min.

Recoverable after 1 hour

Brush and roller: 1 hour

Recoverable after 24 hour.

Peintures ROBIN S.A.

31 rue de la Gare // L-8705 Useldange

T (+352) 23 63 23-1 // F (+352) 23 63 23-58

peintures@robin.lu // www.robin.lu

7 rue Jean Fischbach - Z.a. am Bann // L-3372 Leudelange

T (+352) 49 31 61-1 // F (+352) 49 31 61-880

peintures.standex@robin.lu // www.robin.lu



r o b i n

La qualité en peinture

Technical data sheet
Updated 26.01.2010

Packaging:

Component A: 2L
Component B: 0,5L L-12814 for gun spray
Component B : 0,5L L-18819 for brush and roller.
Marked with a yellow sticker (for 2 components).

VOC :

limit UE for this product (cat.A/j) : 550g/ltr (2007)/500g/ltr(2010)
2KPUfinition (A+B) content max 460g/ltr

Note : This product will not be guaranteed any more if it is tinted by other systems that those of ROBIN S.A.

Foot-note: cancel and replaces the former editions. It is up to our customers to check, before application, that it is indeed the last edition. The information contained in this note has only one indicative range and cannot compensate a description suitable with the nature and the state of the funds to be treated.

Peintures ROBIN S.A.

31 rue de la Gare // L-8705 Useldange
T (+352) 23 63 23-1 // F (+352) 23 63 23-58
peintures@robin.lu // www.robin.lu

7 rue Jean Fischbach - Z.a. am Bann // L-3372 Leudelange
T (+352) 49 31 61-1 // F (+352) 49 31 61-880
peintures.stadox@robin.lu // www.robin.lu