

SC 00021

## **GRASSELLO DI CALCE**

## **Technical Sheet**

NI A MATTA		CE.	
NAME:	GRASSELLO DI CALCE		
TYPE:	mineral mural coating		
<u>USE:</u>	a finishing coating with high degree of transpiration for interior, also those		
TECINICAL DATA.	of historical and artistic importance		
TECHNICAL DATA:	specific weight:	$1.500 \pm 30 \text{ gr/lt}$ at $25^{\circ}\text{C}$	
	viscosity:	===	
	yield:	2-3 m <sup>2</sup> /LT.	
	aspect:	opaque if applied with a brush; glossy if applied and smoothed with a stainless steel trowel	
	colours:	see Rococo' catalogue	
	packaging:	LT.1-LT.4-LT.12	
DRYING TIME:	on the surface:	2 hours at 20 °C	
	over painting:	===	
	below the surface:	18 hours at 20 °C	
CHARACTERISTICS AND	steam permeability: 370 gr/m <sup>2</sup> in 24 hours (UNI 9396 - ISO DIN 7783		
<b>RESISTANCE:</b>	Norm)		
	diffusion resistance factor: $\mu = 120$ (equivalent strata of the air Sd = 0,07		
	m.// thickness of layer = 0,58 mm)		
	water absorbence coefficient: $W = 0,112 \text{ kg/m}^2 \text{ X h}^{0.5}$ (DIN 52617		
	Norm) in accordance with Kuenzle theory: Sd x W < 0,01 kg/m X $h^{0.5}$		
	available coloures: White until 300 kg see Rococo' catalogue for		
	higher quantity		
	colouring: add COLORI available in 80 ML and 480 Ml. packs. Mix		
	using a paint mixing machine at high speed . In order to improve its application colour GRASSELLO a day before use,		
PREPARATION OF THE	All the products in the ROCOCO RANGE must always be applied over		
SURFACE:	their own base coat, PRIMER 200, whether on old or new surfaces.		
SURFACE.	Where there is an existing layer of paint, make sure that it is well anchored to the surface. If not, or if the surface is dusty, remove all the existing		
	paint completely, sand the surface and wash with water and suitable soap.		
		y, apply one coat of PRIMER 200 using a wool	
	roller or a brush and after approximately 8 hours at a temperature of 20°C begin the application cycle for the chosen product in the ROCOCC RANGE.		
PREPARATION OF THE	thinning:	ready for use if applied with stainlass steel	
	timining:	ready for use if applied with stainless steel trowel; to dilute with water if applied with brush	
<u>PRODUCT:</u>	antalization malation.		
	catalization relation:	===	
	pot life:	===	



<u>APPLICATION</u> :	Spread the GRASSELLO DI CALCE with a PV 43, PV 44 or PV stainless trowel, leaving a thickness of product of about 1 mm on surface and leaving the finish smooth and compact. After about 6 hour 20°C, sand well and proceed with spreading the GRASSELLO CALCE with irregular strokes 6 - 10 cm long, spaced 4 - 6 cm apart, of the entire surface to be covered. After about an hour at 20°C, start again from the beginning of the surface root with the first coat, applying strokes as described above, covering the surface, in such a way that each stroke partly overlaps stroke already applied. This is the way to achieve the Semitransparent Antip	the rs at DI over face but okes
	effect.	que
	coats: = = =	
<u>STABILITY:</u>	2 years	

## NOTE:

Wash the tools with water, immediately after using, if paint is dried wash tools mechanically . Application temperature

must not be inferior to +5 and superior to +30 °C. Keep away from sun and wind

Technical Sheet n° SC 00021 issued by the Control Quality Dpt.:

Edition n° 4 Giugno 2008