



robin

La qualité en peinture

Technical data sheet  
Updated : 22/10/2014

## **HYDROSAT** Enamel, dilutable with water

**COMPOSITION:** 100% acrylic resin dispersed in water

**ASPECT:** satin

**PROPRIETES AND APPLICATION:**

- the HYDROSAT enamel possesses an excellent coverage. Its spreadability is perfect and due to its long opening time, it guarantees a nice tense and results in a high quality work
- HYDROSAT can be applied on all internal and external surfaces: metal, wood, plaster, concrete, MDF, etc. All supports need to be pre-treated with HYDROGRIP or HYDROFACER.
- Very good washability Class 1 according to ISO 11998
- Solid content: 46 %
- Density: 1,29
- Brilliance: 35 % NOVOGLOSS RHOPOINT 60 °
- VOC : 28,5 g/l

**INSTRUCTION FOR USE:**

HYDROSAT is applied with a brush or roller in two successive layers.  
Dilute with 2 % of water when using a brush or roller.  
Do not dilute when using airless paint sprayer.  
Dilute with 5% of water when using the HVLP-sprayer.

**DRYING:** recoatable after 4 hours

**CLEANING:** with water

**CONSUMPTION:** 8 - 10 m<sup>2</sup>/ltr

**Colour shades:**

All RAL and ROBIN-MIX shades are available, all others on demand

**PACKAGING:** 750 ml – 2,5 ltr – 12,5 ltr

**NOTE:** protect from frost

**VOC :** EU limits for this products (cat.IIA/d) : 130g/l(2010), the current value for Hydrosat is 18g/l.

Explanatory note : This product will not be guaranteed anymore if it is tinted by other systems than those of ROBIN S.A.  
*Note: cancels and replaces former editions. It is up to our customers to check, before application, that this is indeed the last edition. The information contained in this note has only one indicative range and cannot compensate a description suitable with the nature and the state of the funds to be treated.*

**Peintures ROBIN S.A.**

31 rue de la Gare // L-8705 Useldange  
T (+352) 23 63 23-1 // F (+352) 23 63 23-58  
[peintures@robin.lu](mailto:peintures@robin.lu) // [www.robin.lu](http://www.robin.lu)

7 rue Jean Fischbach - Z.a. am Bann // L-3372 Leudelange  
T (+352) 49 31 61-1 // F (+352) 49 31 61-880  
[peintures.standex@robin.lu](mailto:peintures.standex@robin.lu) // [www.robin.lu](http://www.robin.lu)