



SC 00023

INTONACHINO MINERALE

Technical Sheet

NAME:

INTONACHINO MINERALE

TYPE:

mineral mural covering for exterior

USE

as finish to restore historical buildings.

TECHNICAL DATA:

specific weight : 1.700 ± 30 gr/LT. at 25°C

viscosity: = = =

yield: 0,600-0,700 m²/LT. on smooth surface

aesthetic aspect: opaque with shading chromatics aspects

colours: see Rococò catalogue

packaging: LT. 12

DRYING TIME:

on the surface: 2 hours at 20°C

over painting: 4-6 hours at 20°C on the basis of the applied thickness

below the surface: = = =

CHARACTERISTICS AND RESISTANCE:

water vapour permeability: 33,3 gr/m² in 24 hours
(norm UNI 9396 and ISO/DIN 7783)

diffusion resistance factor : $\mu = 881$ equivalent air layer

$S_d = 0,65$ m

(dried thickness of the paint layer 0,73 mm)

water absorption coefficient: $W = 0,29$ Kg/m² x h^{0,5}

(norm DIN 52617)

in accordance with Kuenzle theory: $S_d \times W \leq 0,2$ kg/m x h^{0,5}

(norm Din 18550)

colouring: add COLORI available in 80 ML and 480 ML. packs. Mix using a paint mixing machine at high speed . In order to improve its application colour GRASSELLO a day before use,

PREPARATION OF THE SURFACE:

All the products in the ROCOCO RANGE must always be applied over their own base coat, PRIMER 200, whether on old or new surfaces.

Where there is an existing layer of paint, make sure that it is well anchored to the surface. If not, or if the surface is dusty, remove all the existing paint completely, sand the surface and wash with water and suitable soap. When the surface is dry, apply one coat of PRIMER 200 using a wool roller or a brush and after approximately 8 hours at a temperature of 20°C, begin the application cycle for the chosen product in the ROCOCO RANGE.

PREPARATION OF THE PRODUCT:

dilution: ready to use

catalyses relation: = = =

pot life: = = =

APPLICATION:

Spread a coat of INTONACHINO ALLA CALCE with a PV 43, PV 44 or PV 45 stainless trowel, and refinish, while the surface is still wet, with the PV 46 sponge trowel or a plastic trowel, with circular movements.

To obtain a smoother and more uniform finish, wait several minutes until the product is in tension before proceeding to the finish with the sponge trowel.

numbers of coats: = = =



NOTES:

Wash the tools with water, immediately after using, if paint is dried wash tools mechanically. Application temperature must not be inferior to +5°C and superior to +30°C.
Keep away from sun and wind

Technical Sheet n° SC 00023 issued by the Control Quality Department:

Edition n°3 Octobre 2006

page 2 of 2