



robin

La qualité en peinture

Technical data sheet
Updated : 10/04/2013

MARTOLAC

DESCRIPTION:

Fast drying alkyd enamel.

PROPRIETES ET UTILISATION:

MARTOLAC enamel is giving a hammered effect.

Generally applied on metallic coatings or pretreated with olive yellow Ferroprimer L-2203. Can also be applied on wood, covered with a layer of Unifacer.

Appearance: shiny hammered

Viscosity: 80 dry according to DIN 53 212 4 mm

Drying time: dust-free: 5 to 10 min.
Dry: 2 hours.

Recovering possible after 24 hours.

PE 21 °C

INSTRUCTIONS:

MARTOLAC is ready for use.

It may nevertheless be diluted with 2% max. of synthetic Thinner for brush and roll applying and with 5% max. synthetic Thinner for applying by pistol.

CLEANING AND DILUTION: White Spirit or synthetic Thinner.

COVERAGE: 8 - 10 m²/ltr with 30 - 40 µm film dry.

PACKAGE: 250 ml – 750 ml – 2,5 ltr

VOC : Valeurs limites pour ce produit (cat.IIA/i) : 600g/l (2007) – 500g/l (2010)
Le Martolac contient 429g/l VOC

Remarque : Warranty invalid, if other system than provided by ROBIN S.A. is used

Nota : cancel and replaces the former editions. It's up to our customers to check, before application, if it is indeed the last edition. The information contained in this note has only one indicative range and can not compensate a description suitable with the nature and the state of funds to be treated.

Peintures ROBIN S.A.

31 rue de la Gare // L-8705 Useldange
T (+352) 23 63 23-1 // F (+352) 23 63 23-58
peintures@robin.lu // www.robin.lu

7 rue Jean Fischbach - Z.a. am Bann // L-3372 Leudelange
T (+352) 49 31 61-1 // F (+352) 49 31 61-880
peintures.standex@robin.lu // www.robin.lu