



robin

La qualité en peinture

Technical data sheet
Updated: 14/08/2014

ROBINSILK

COMPOSITION: thixotropic urethane alkyd enamel

APPEARANCE: Silk

PROPERTIES AND APPLICATION:

Silk enamel with a thixotropic consistency.

After application of prime, applicable on all surfaces : wood, metal, plaster and so on.

After lightly having dried, surfaces need to be pretreated with a layer of UNIFACER.

ROBINSILK guarantees an excellent coverage and excellent tence.

INSTRUCTIONS FOR USE:

ROBINSILK is applied with a brush, roller or paint sprayer. A light dilution may be achieved with White Spirit.

Add 15% of White Spirit, when using with the paint sprayer with either high or low pressure

DRYING :

Dust-free : 2 - 3 hours

Dry : 5 - 6 hours

Hard after : 24 hours

CLEANING AND DILUTION: with White Spirit

CONSUMPTION 10 - 12 m² / litre

COLOUR SHADES:

ROBINSILK is available in all shades on shades of our ROBIN-MIX card or other tints on demand.

PACKAGING : 250 ml (white and all shades of the card) - 750 ml – 2,5 ltr – 5 ltr – 20 ltr

VOC : EU limits for this product (cat.IIA/d) : 300 g/l(2010)
Robinsilk < 300 g/l de VOC

If applied on a substrate without daylight the paint can be subject to yellowing. This is a natural reaction of the resin. Robin can not be hold responsible for this.

Explanatory note : This product will not be guaranteed anymore if it is tinted by other systems than those of ROBIN S.A.

Note: cancels and replaces former editions. It is up to our customers to check, before application, that this is indeed the last edition. The information contained in this note has only one indicative range and cannot compensate a description suitable with the nature and the state of the funds to be treated.

Peintures ROBIN S.A.

31 rue de la Gare // L-8705 Useldange

T (+352) 23 63 23-1 // F (+352) 23 63 23-58

peintures@robin.lu // www.robin.lu

7 rue Jean Fischbach - Z.a. am Bann // L-3372 Leudelange

T (+352) 49 31 61-1 // F (+352) 49 31 61-880

peintures.standex@robin.lu // www.robin.lu